Hydrogen Back Pressure Effects on the Dehydrogenation Reactions of $Ca(BH_4)_2$

†‡*Yoonyoung Kim*, §*Son-Jong Hwang*, †*Young-Su Lee*, †*Jin-Yoo Suh*, ‡*Heung Nam Han, and* †*Young Whan Cho*

†High Temperature Energy Materials Research Center, Korea Institute of Science and Technology, Seoul 136-791, Republic of Korea, ‡Department of Materials Science and Engineering, Seoul National University, Seoul 151-742, Republic of Korea, §Division of Chemistry and Chemical Engineering, California Institute of Technology, Pasadena, California 91125, USA

* Corresponding author:oze@kist.re.kr

Supporting Information:

Figure S1. ^{11}B MAS NMR spectrum of amorphous boron (Aldrich) and its spectral decomposition into two major peaks at 4.5 ppm and -16 ppm. The distribution of two peaks is in a 4:1 ratio according to the signal integration.



Figure S2. ^{11}B MAS NMR spectra with decomposition into CaB_6 (broken line at 14 ppm), elemental boron (blue solid line at 4.5 ppm and -16 ppm), $CaB_{12}H_{12}$ (broken line at -15.6 ppm), and $Ca(BH_4)_2$ related unidentified amorphous phase (green solid lines at -32 ppm and -40 ppm)